



TEST REPORT

100 Clemson Research Blvd.
Anderson, SC 29625
(864) 656-1094
Fax: (864) 656-1095
www.brickandtile.org

Results of Tests on brick Conducted in accordance with ASTM C 67-16 Standard Test Methods for Sampling and

Testing Brick and Structural Clay Tile

07/12/2017

Name:	Pacific Clay Products Inc 14741 Lake Street Lake Elsinore , CA 92530-1609	Plant:	Pacific Clay Products	*Temperature: 60 - 90F
Phone:	951-674-2131 Ext119	Report Number:	7649-16844	*Humidity: 30% - 70%
Fax:		Received Date:	06/29/2017	
		Sampled Date:	06/29/2017	
		Lot:		
		Product Code:		

Sample Description: **3 5/8" x 1 1/4" x 7 5/8" Sterling Gray**

						Average	Test Date
Absorption	1	2	3	4	5		
24 Hour Submersion in Cold Water (%)	7.01	6.47	6.61	7.18	6.35	6.72	07/05/2017
5 Hour Submersion in Boiling Water (%)	9.15	8.47	8.67	9.31	8.35	8.79	
Saturation Coefficient (Ratio of 24H to 5H)	0.77	0.76	0.76	0.77	0.76	0.76	
Compressive Strength	1	2	3	4	5	Average	
<i>psi</i>	13,264	16,597	14,589	13,920	16,072	14,888	07/05/2017
<i>MPa</i>	91.4	114.4	100.6	96.0	110.8	102.7	
Breaking Load	6	7	8	9	10	Average	
<i>(lb/in.)</i>	181	196	189	220	213	200	07/11/2017
Efflorescence	11	12	13	14	15		
	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced	Not Effloresced		07/10/2017
IRA (Oven Dried Method)	6	7	8	9	10	Average	
<i>g/min/30 in.²</i>	22.4	22.1	22.8	18.8	20.1	21.2	07/05/2017
Abrasion Resistance	1	2	3	4	5	Average	
	0.05	0.04	0.05	0.05	0.04	0.05	07/05/2017

The brick represented by the test results shown here comply with the physical property requirements of the standards listed below:

ASTM C 902 - 15 Standard Specification for Pedestrian and Light Traffic Paving Brick

Class: SX, MX, NX

Type: I, II, III

Michael Walker, Quality Manager

**The temperature and humidity of the Bishop Materials Laboratory is constantly kept between 60 -90F, and 30-70% RH
The results shown above apply only to the samples tested, which are provided by the customer.
This test report shall not be reproduced except in full, without written approval of the laboratory.*